temperature of about ≤ 1525°C ± 5°C or below, the glass-ceramic having a composition, in weight percent on an oxide basis, consisting essentially of about: 40-60% SiO₂; 10-25% Al₂O₃; 18-30% MgO; 3-10% Na₂O; 0-10% K₂O; and >5-15% TiO₂.

<u>REMARKS</u>

Claims 21-32 remain in this application. Claims 1-20 and 33-42 have been canceled. New claim 43 has been added.

The Assistant Commissioner is hereby authorized by CORNING INCORPORATED to charge any additional fees that may be required by this paper to Deposit Account No. 03-3325.

Please direct any questions or comments to Vincent T. Kung at (607) 974-0608.

September 29, 2003

Vincent T. Kung

Date

CERTIFICATE OF MAILING UNDER 37 C.F.R. § 1.10

Date of Deposit: September 29, 2003

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R. 1.10 on the date indicated above and is Addressed to the Commissioner of Patents and Trademarks, Washington,

September 29, 2003

"EXPRESS MAIL" Mailing Label No. EV327188055US

Respectfully submitted,

CORNING INCORPORATED

Vincent T. Kung

Attorney for Assignee Registration No. 45,797

Corning Incorporated

Patent Department

Mail Stop SP-TI-03-1

Corning, NY 14831